

Durethan DP AKV 30 FN00

PA 66, injection molding 30 % glass fibers, UL 94 V-0 at 0.4 mm, max. temperature in glow wire test: 960 °C at 0,75 mm, free from halogen and red phosphorous

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Rheological properties					
C Molding shrinkage, parallel	60x60x2; 270 °C / WZ 80 °C; 600 bar	%	ISO 294-4	0.2	
C Molding shrinkage, transverse	60x60x2; 270 °C / WZ 80 °C; 600 bar	%	ISO 294-4	0.7	
Post- shrinkage, parallel	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.1	
Post- shrinkage, transverse	60x60x2; 120 °C; 4 h	%	ISO 294-4	0.1	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	10500	6500
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	135	85
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	2.8	5.4
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	55	57
Izod notched impact strength		kJ/m ²	ISO 180-1A	10	
Flexural modulus	2 mm/min	MPa	ISO 178	9300	5600
Flexural strength	2 mm/min	MPa	ISO 178	215	135
Flexural strain at flexural strength	2 mm/min	%	ISO 178	3.1	5.2
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178		120
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	260	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	224	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	>250	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	240	
C Burning behavior UL 94 (1.6 mm)	1.5 mm	Class	UL 94	V-0	
C Burning behavior UL 94	0.4 mm	Class	UL 94	V-0	
C Burning behavior UL 94	3.0 mm	Class	UL 94	V-0	
Glow wire test (GWFI)	0.8 mm	°C	IEC 60695-2-12	960	
Glow wire test (GWFI)	1.5 mm	°C	IEC 60695-2-12	960	
Glow wire test (GWFI)	3.0 mm	°C	IEC 60695-2-12	960	
Glow wire test (GWIT)	0.75 mm	°C	IEC 60695-2-13	725	
Glow wire test (GWIT)	1.5 mm	°C	IEC 60695-2-13	725	
Glow wire test (GWIT)	3.0 mm	°C	IEC 60695-2-13	725	
Electrical properties (23 °C/50 % r. h.)					
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	600	
Other properties (23 °C)					
C Density		kg/m ³	ISO 1183	1417	
Glass fiber / glass bead / filler content		%	ISO 3451-1	30	



Durethan DP AKV 30 FN00

Property	Test Condition	Unit	Standard	Value	d.a.m.	cond.
Processing conditions for test specimens						
C Injection molding-Melt temperature		°C	ISO 294	270		
C Injection molding-Mold temperature		°C	ISO 294	80		
Processing recommendations						
Drying temperature		°C	-	80		
Drying time dry air dryer		h	-	2-6		
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.07		
Melt temperature		°C	-	260-270		
Mold temperature		°C	-	80-100		

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Durethan DP AKV 30 FN00

Disclaimer

Disclaimer for developmental products

Trial Products (grade designations beginning with the codes DP, TP, KL or KU) This is a Sales Product at the developmental stage (a Trial Product). For this reason, no assurances can be given as to type conformity, processability, long-term performance characteristics or other production or application parameters. No definitive statements can be made regarding the behavior of the product during processing or use. The purchaser/user uses the product entirely at his own risk. The marketing and continued supply of this material are not assured and may be discontinued at any time. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

LANXESS DEUTSCHLAND GMBH | D - 51369 LEVERKUSEN

© LANXESS Deutschland GmbH

